

# הופכים כל רחבה למגרש מקצועי: פתרונות הקמה לטורנירי סטריטבול ו-3X3


מגרשי כדורסל מודולריים בסטנדרט הבינלאומי הגבוה ביותר. מהירות הקמה, בטיחות מקסימלית וחווית משחק של ליגת ה-FIBA – אצלכם בעיר.

## מה כולל השירות

### הפתרונות שלנו מותאמים לצרכים של עירויות, מפיקי אירועים ומועדוני ספורט:

- **טכנולוגיית ריצוף מודולרי:** אריחי TPE מתקדמים המעניקים בלימת זעזועים להגנה על קרסולי השחקנים וחווית "ריבאונד" כדור מושלמת.
- **Ready for Rain:** מבנה הניקוז הייחודי של המשטחים מאפשר חזרה למשחק דקות בודדות לאחר הגשם – ללא שלוליות וללא סכנת החלקה.
- **מערכות סלים הידראוליות וניידות:** סלים מקצועיים עם לוחות זכוכית מחוסמת, ריפוד בטיחותי עבה וטבעות קפיציות (Breakaway) לעמידות בביצוע הטבעות.
- **מיתוג ושיווק על המגרש:** אפשרות לשילוב לוגו הטורניר או נותני החסות ישירות על גבי המשטח (In-floor branding) ליצירת נראות טלוויזיונית ויוקרתית.

מאפיין	מפרט טכני	יתרון למארגן
סוג משטח	אריחי TPE	מניעת החלקה ועמידות UV
בלימת זעזועים	גמישות רוחבית מובנית	צמצום משמעותי של פציעות שחקנים
זמן הקמה	4-6 שעות למגרש מלא	חיסכון בעלויות תפעול ולוגיסטיקה
ציוד היקפי	סלים ניידים מאסיביים	גמישות מלאה במיקום המגרש



## FIBA Approval Programme for Basketball Equipment

## Laboratory Test Report – 3x3 &amp; Outdoor

Results Summary			
Performance Property	Results	Requirement	Pass/ Fail
Force Reduction	32%	Point-elastic L1: 25% - 75%	PASS
Force Reduction Uniformity (absolute)	0%/+1%	Point-elastic L1: $\pm 5\%$ from average	PASS
Vertical Deformation	3.0mm	Point-elastic: $\leq 3.5\text{mm}$	PASS
Vertical Deformation Uniformity (absolute)	-0.2mm/+0.2mm	$\pm 0.7\text{mm}$ from average	PASS
Ball Rebound	96%	Level 1: $\geq 90\%$	PASS
Ball Rebound Uniformity	-1%/+2%	$\pm 3\%$ from average	PASS
Slip Resistance (Dry)	92	Average: $\geq 80 \leq 110$	PASS
Slip Resistance (Wet)	45	Average: $\geq 55 \leq 110$	Not suitable for wet conditions
Resistance to Wear	230mg	$\leq 1000 \text{ mg}$	PASS
Assembly/Disassembly Mechanism Durability	No visible deterioration	No visible deterioration	PASS
UV Resistance - Resistance to Impact	No damage before weathering	Pre-weathering: Informative only	Informative - No presence of cracking
	No damage after weathering	Post-weathering: Informative only	Informative - No presence of cracking
UV Resistance - Colour Fastness	Greyscale 4-5	Post-weathering: Informative only (Guidance: $\geq$ Greyscale 3)	Informative
Dimensional Stability	0.21%	$\leq 1\%$	PASS
Water Permeability	$> 10,000$	Permeable surface: $\geq 150 \text{ mm/h}$	PASS
Court Markings	All measurements are within the required tolerance	$\pm 5\text{mm}$ of the requirements	PASS
Summary notes: -			